A1

PATENT ABSTRACTS OF JAPAN

(11)Publication number:

06-228011

(43)Date of publication of application: 16.08.1994

(51)Int.Cl.

A61K 47/02 A61K 9/00

(21)Application number: 04-248774

(71)Applicant: OTSUKA MAKOTO

KYORITSU YOGYO GENRYO KK

S T K CERAMICS KENKYUSHO:KK

(22)Date of filing:

25.08.1992

(72)Inventor: (

OTSUKA MAKOTO

MATSUDA YOSHIHISA

(54) CALCIUM PHOSPHATE-BASED SUSTAINED RELEASE MATERIAL FOR DRUG AND ITS PRODUCTION

(57)Abstract:

PURPOSE: To obtain a sustained release material for drug capable of more firmly bonding and keeping a drug in a hard biotissue, easily controlling the releasing rate of the drug and getting a more effective sustained release effect and to provide a production method for the sustained release material.

CONSTITUTION: Tetracalcium phosphate is compounded with hydrogen calcium phosphate or its dihydrate at a ratio to get a molar Ca/P ratio corresponding to that of the hydroxyapatite composition and the obtained self-curable calcium phosphate cement composition is used as a base for holding a drug. The calcium phosphate cement composition is incorporated with 25-70wt.% of an aqueous solution of phosphoric acid having a concentration of 0.1-0.3 m-mol/L and the mixture is kneaded and cured to obtain a cured material having a void ratio controlled to 20-60% and having controlled releasing rate of the drug maintained in the cured material.

LEGAL STATUS

[Date of request for examination]

03.06.1999

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

3170059

[Date of registration]

16.03.2001

rejection]
[Date of requesting appeal against examiner's decision of rejection]
[Date of extinction of right]

[Number of appeal against examiner's decision of

Copyright (C); 1998,2003 Japan Patent Office